

# **BOBST**

## Technical Data Sheet

**Product:** Bobst PROject Series Ejection Material

**Product Name:** PROject 75

**Compares to:** T75

**Color:** Blue

**Size:** 18" x 18" +/- 1/4"

**Thickness:** .375" +/- 3.5%

**Product Benefits and Usage:** Longer life and more consistency than its competitor.

**Product Characteristics:** Third (3<sup>rd</sup>) party testing data provided by Huntsman Chemical (Detroit, Mi.)

**Hardness (Shore A):**

- **Bobst PROject 75:** 37
- **T75:** 37

**Resiliency (Ball Rebound):**

- **Bobst PROject 75:** 41%
- **T75:** 35%

**Compression Set:** Compressed to 50% of original thickness and held for 24 hours and measured to determine % loss.

- **Bobst PROject 75:** .9%
- **T75:** 6.5%

**Dynamic Fatigue:** Sample reduced by 25% of original thickness by subjecting to continuous compression for 100,000 cycles and measured to determine % loss.

- **Bobst PROject 75:** 0%
- **T75:** 2.6%

**Bobst Group North America, Inc.**

146 Harrison Avenue  
Roseland NJ 07068-1294, USA  
Tel.: +1 973 226 8000  
Fax: +1 973 226 8625

**Bobst SA**

PO Box, CH-1001 Lausanne  
Tel.: +41 21 621 21 11  
Fax: +41 21 621 20 70

[www.bobstgroup.com](http://www.bobstgroup.com)

